



## Alternative Natural Deliming Agents<sup>1</sup>

Eser Eke Bayramoglu<sup>1</sup>, Seda Erdogan Bayram<sup>2</sup>

<sup>1</sup>Department of Leather Engineering, Faculty of Engineering, Ege University, 35100, Izmir, Turkiye, Phone: +90 5053974542, Fax: +90 2323425376, e-mail: eser.eke@ege.edu.tr, eserekebay@gmail.com

<sup>2</sup>Central Laboratory of Agricultural Faculty, Ege University, 35100, Izmir, Turkiye, Phone: +90 5063670444, e-mail: seda.erdogan@ege.edu.tr

### ABSTRACT

This study elucidates whether the herbal extracts can be used instead of various chemical substances used in the process of deliming. To that end, the extracts of christ's thorn seed (*Paliurus spina-christi*), red radish (*Raphanus sativus var. radicola*) and black radish (*Raphanus sativus var. niger*) were employed in the deliming process. Calcium content of the leathers has been identified with Perkin Elmer Optima 2100 DV ICP-OES (Inductively Coupled Plasma- Optical Emission Spectrometry). As a result of the controls carried out, it was concluded that red radish and especially black radish extract have a considerable deliming effect. SEM images of the grain surface are also shown in this paper.

**Keywords:** Leather, deliming, *Raphanus sativus var. niger*, *Raphanus sativus var. radicola*.

### 1. Introduction

The purpose of deliming is to neutralise the alkali, lime etc. from the liming process thus causing the skin to become flaccid by releasing the bound water from the swollen protein fibre. Generally ammonium sulphate is used due to its low-cost. <sup>1</sup> Ammonium sulphate is a white color fertilizer with  $(\text{NH}_4)_2\text{SO}_4$  physiological acid character and also containing 21% nitrogenous plant nutrient. It has very high buffering capacity, gives also very clean pelts with fine grain and will not cause problems if overdosed. During deliming with ammonium salts the PH is reduced for bating to use pancreatic bating agents at pH 8.0-9.0. Ammonia is however a pollutant both in the waste water and as an atmospheric pollutant due to the free ammonia released during deliming and bating. <sup>1</sup> The excessive mixing of ammonium sulphate to soil and water causes to the pollution of ground and surface waters, to air pollution with nitrogen oxide emission, to the deformation of soil structure, modification of soil reactions and damaging the balance of the elements in the soil, and in this context, to damaging the macro and micro fauna in the soil. In addition, when these compounds with nitrogen content diffuse in the environment excessively, the nitrate amount on the leaf reaches a level which threatens the human health especially on the vegetables with edible leaves. <sup>2</sup>

Together with the diffusion of these compounds into soil at high quantities, their conversion into nitrate by nitrification due to microorganisms, and because of the negative charge of nitrate, they are washed from the soil, thus causing to a high amount of nitrogen in ground waters. This increases the acidity of the soils with low acidity and acidic reaction, thus also increasing the solubility of the elements such as Al and Mn, and causing to the appearance of toxicity of these elements in the plant. <sup>3</sup> In addition, they accumulate in the soil and expand the size of soil pollution. The importance of the excessive mixing of these nitric compounds into soil in terms of soil microbiology is that they negatively impact the activities of symbiotic microorganisms which fix the free nitrogen in air such as

---

<sup>1</sup> This study has partially been extracted from Mümin Çolakoğlu, Murat Kaplan and Demet Şahin's bachelor dissertation study which entitled 'Bazı Bitki Ekstraktlarının Kireç Giderme İşleminde Kullanılabilirliğinin Araştırılması'



**Rhizobium sp.** In this case, the way of benefitting from the free nitrogen of air is blocked. As a result, the nitrogen compounds which mix in soil at high amounts limits the activities of nitrification bacteria, and damages the second source of nitrogen which is ready and cost-free (the free nitrogen in air).<sup>4</sup>

Currently, the processes under the title ecologic leather products include natural products which do not harm the environment and human health, and alternative technologies are being developed. Although the use of chemicals is highly common during the deliming stage, which is one of the steps of leather processing, the studies for the use and development of different products for a sustainable ecological production are conducted.<sup>1, 5, 6, 7</sup>


In this research, herbal extracts have been used instead of the chemical agents used during the deliming stage, and their deliming effects have been examined. For this purpose, Christ's torn seed, red radish and black radish extracts have been employed in the study. Historically this plants have been used as medicinal foods for a variety of ailments such as kidney stone expellers and gallstone expellers.<sup>8,9,10,11</sup> Setting up from here, the study aims to identify the deliming activities of the mentioned herbal agents in the leather industry.

## 2. Materials and Methods

### 2.1. Materials

#### 2.1.1. Plant Extracts

Radishes (*Raphanus sativus* L.) are members of the cruciferous vegetable family which contain many classes of biologically active phytochemicals. There is a great diversity in the cruciferous vegetable family, and radishes themselves are available in varieties that differ in terms of size, shape, and colour. In this study black (*Raphanus sativus* var. *niger*) and red radishes (*Raphanus sativus* var. *radicula*) were used. For the aims of the study, the squeezed juice was obtained from radishes and dried. These extracts were used for the experiments. In folk medicine the black and red radishes have been used since antiquity as a natural drug against abdominal inflation, insufficient digestion and for the inhibition of gallstone formation etc.<sup>12</sup> It was reported that these plants contain sulfur-containing secondary metabolites known as glucosinolates (GLs) and /or their derivatives ( isothiocyanates, nitriles, cyano-epithioalkanes formed during hydrolises catalysed by myrosinase), essential oils, flavanoids and other polyphenolic compounds.<sup>13,14,12</sup>



**Figure 1.** Structures of the primary glucosinolates found in radish varieties.<sup>13</sup>



It was reported that black radish root contains a high level of different glucosinolates (1029 mg/100g)<sup>15</sup> but some researchers reported that they found only glucotropaeolin and it is supposed that during processing and storage, the enzyme myrosinase is activated and all the glucosinolates are hydrolysed to degradation products such as bisothicyanates, nitriles, thiocyanates, oxazolidinethiones, sulphate and glucose.<sup>12,16</sup> Recently, a number of studies have demonstrated that radishes or radish extracts have biological activity including antioxidant<sup>10,17</sup> antimutagenic<sup>18</sup> and fungitoxic activity.<sup>19</sup> The christ's thorn plant used in the study was picked in the Ege University (Izmir) campus area. The collected seeds were dried in a damp-free room without being exposed to sunlight. The seeds were grinded and destructed, and the grinded seeds of the christ's torn plant were placed on a heater together with a stirrer, and thus the extraction was realized. Then the extract was powdered.

### 2.1.2. Skin

In the study, sheep raw skins (wet-salted) were used. The applications were carried out on the leathers with two different structures. Of these leathers, the first one is thick and strict in structure, and the second one is thin and limp in structure.

## 2.2. Methods

### 2.2.1. Processing of raw skin

The leathers were processed in compliance with a standard recipe until the deliming process. After that, each of the prepared extracts was used at 4% in the deliming process. At the end of 90 and 120 minutes, the control was made with phenolfitalein and the effectiveness of the used extracts were examined.

### 2.2.2. Calcium Analysis of leathers

The leathers weighed at around 0.5 gr precision, were processed through concentrated HNO<sub>3</sub> 5 ml and concentrated HClO<sub>4</sub> wet decomposition process and the Ca<sup>2+</sup> amount in the samples diluted to 25 ml was identified with Perkin Elmer Optima 2100 DV ICP-OES (Inductively Coupled Plasma- Optical Emission Spectrometry) at recommended parameters and wavelengths. The operating conditions of the instrument are provided in Table 1.

**Table-1.** The conditions of ICP-OES

Wavelength (Ca <sup>2+</sup> ) nm.	Plasma (L/min)	Aux (L/min)	Neb (L/min)	Power Watts	Plasma View	View Dist
317.933	17	0,20	0,80	1450	Axial	15

The analyses have been repeated twice on both thick and thin leathers and deliming with ammonium sulphate was compared with the commercially available Mixture of inorganic salts, acids and buffering ammonium salts based deliming agent, and the control sample.

### 2.2.2.3. Identification of Thickness of Leathers

Satra thickness gauge is used.



## 2.2.4. Scanning Electron Microscope (SEM)


Hitachi Model TM-1000 Tabletop Microscope was used to obtain SEM images.

## 3. Results and Discussion


The calcium content and leather thicknesses identified on the leathers with ICP-OES are listed on Table 1.

**Table 2-** Calcium content of the leathers and thickness

<i>Leather sample</i>	<i>Ca<sup>2+</sup> Content (ppm)</i>	<i>Thickness (mm)</i>
Control sample (Thick)	945.7	1.78
Control sample (Thin)	920.1	1.53
<i>Paliurus spina-christi</i> (Thick)	974.5	2.34
<i>Paliurus spina-christi</i> (Thin)	934.8	1.47
<i>Raphanus sativus</i> var. <i>radicula</i> (Thick)	900.3	1.95
<i>Raphanus sativus</i> var. <i>radicula</i> (Thin)	880.4	0.93
<i>Raphanus sativus</i> var. <i>niger</i> (Thick)	853.2	1.81
<i>Raphanus sativus</i> var. <i>niger</i> (Thin)	772.4	1.13
Ammonium sulphate (Thick)	795.7	1.14
Ammonium sulphate (Thin)	797.5	0.85
Deliming agent (Thick)	749.7	1.46
Deliming agent (Thin)	749.6	1.04



**Figure 2.** Calcium content of thick leathers



**Figure 3.** Calcium content of thin leathers

1. Control sample
2. *Paliurus spina-christi*
3. *Raphanus sativus* var. *radicula*
4. *Raphanus sativus* var. *niger*
5. Ammonium sulphate
6. Deliming agent

On the 90<sup>th</sup> and 120<sup>th</sup> minutes of deliming process, deliming activities were checked with phenolphthalein, and the results obtained accordingly are shown on Table 3, 4, 5 and 6.



**Table 3.** The effect of used plant extracts on thick leathers at the end of 90 minutes

Extract type	pH value after process	Cross section color (Control with phenolfitalein)	Deliming effect
<i>Paliurus spina-christi</i>	>8.2	Pink	None
<i>Raphanus sativus var. radicula</i>	>8.2	Light pink	Little
<i>Raphanus sativus var. niger</i>	>8.2	Very light pink	Good
Control (wash only with water)	>8.2	Dark pink	Bad
Ammonium sulphate (1,5 %)	8.2	Colorless	Very good
Deliming agent (1,5 %)	8.2	Colorless	Very good

**Table 4.** The effect of used plant extracts on thick leathers at the end of 120 minutes

Extract type	pH value after process	Cross section color (Control with phenolfitalein)	Deliming effect
<i>Paliurus spina-christi</i>	>8.2	Light pink	Little
<i>Raphanus sativus var. radicula</i>	>8.2	Very light pink	Little
<i>Raphanus sativus var. niger</i>	<8.2	Colorless	Very good
Control (wash only with water)	>8.2	Dark pink	Bad
Ammonium sulphate (1,5 %)	8.2	Colorless	Very good
Deliming agent (1,5%)	8.2	Colorless	Very good

**Table 5.** The effect of used plant extracts on thin leathers at the end of 90 minutes


Extract type	pH value after process	Cross section color (Control with phenolfitalein)	Deliming effect
<i>Paliurus spina-christi</i>	>8.2	Light pink	Little
<i>Raphanus sativus var. radicula</i>	>8.2	Light pink	Little
<i>Raphanus sativus var. niger</i>	>8.2	Very light pink	Good
Control (wash only with water)	>8.2	Dark pink	Bad
Ammonium sulphate (1,5 %)	8.2	Colorless	Very good
Deliming agent (1,5 %)	8.2	Colorless	Very good

**Table 6.** The effect of used plant extracts on thin leathers at the end of 120 minutes


Extract type	pH value after process	Cross section color (Control with phenolfitalein)	Deliming effect
<i>Paliurus spina-christi</i>	>8.2	Very light pink	Good
<i>Raphanus sativus var. radicula</i>	<8.2	Colorless	Very good
<i>Raphanus sativus var. niger</i>	<8.2	Colorless	Very good
Control (wash only with water)	>8.2	Dark pink	Bad
Ammonium sulphate (1,5 %)	8.2	Colorless	Very good
Deliming agent (1,5 %)	8.2	Colorless	Very good



During the researches conducted, SEM images of the leathers were obtained through enlarging by 80 times. Especially, as also clearly noted on the images, certain changes occurred on the skin structure of thin and thick leathers depending on the given agent. Especially, a thickening of the leather and coarsening on the leather skin was observed as anticipated when *Paliurus spina-christi* extract in polyphenolic structure was given to the leather during the deliming stage. As a result of deliming of the leather with water, deliming could not be realized completely, and cracks occurred on the surface, especially veining occurred on thick leather. Herbal agents give the leather their own peculiar colors, while a thin, leaning and clean leather was obtained after the process done with ammonium sulphate and commercial deliming agent. As a result of processing with black radish, a thin skin was obtained, but it gave the skin a yellowish color.




**Figure 4:** Deliming with ammonium sulphate thin and thick leathers SEM images x80




**Figure 5:** Deliming with *Raphanus sativus* var. *niger* thin and thick leathers SEM images x80







**Figure 6:** Deliming with *Raphanus sativus* var. *radicula* thin and thick leathers SEM images x80



**Figure 7:** Control groups- Deliming with water thin and thick leathers SEM images x80



**Figure 8:** Deliming with industrial deliming agent thin and thick leathers SEM images x80



**Figure 9:** Deliming with *Paliurus spina-christi* thin and thick leathers SEM images x80

## Conclusions

Industrialization rapidly accelerates as a result of the never-stopping advancement of modern technologies in our era, and global competition among countries climbs day by day. However the human life- and environment-threatening extent of the waste amount, which has been highlighted prominently in recent years, has become a serious issue that requires measures being taken. The use of natural products instead of the chemical agents used in processes for the sake of protecting the human- and environmental-health is being researched and tried to be implemented also in the leather industry similar to all other branches of industry. This study inspected whether natural agents would be used instead of chemical preparations during deliming process as one of leather processing steps, and reached certain positive results. It has been identified that the black radish extract has a high deliming impact, while red radish extract is also effective, but not as much as black radish. Especially for the leather types without thick structures, black radish extract may be an alternative to other commercially available preparations. According to the literature study we conducted, it is known from many researches that radish extracts contain glucosinolates (GLs). Glucosinolates are important thiosaccharidic metabolites and the researches on their synthetic production are currently ongoing. As a further step to this study, the active compound in the radish extract should be identified, and synthetic means of production of this substance, its economic worth, environmental importance, advantage and disadvantage for leather industry should be scrutinized.

## References

1. Reeder, F., Chapter 3: Modern Beamhouse Procedure Deliming and Bating, Leather Technologists Pocket Book, pg:37-38,1999.
2. Ceran, Y., Kimyasal gübreler ve toprak. Çevre Koruma Genel Müdürlüğü, Çevre ve İnsan dergisi, Vol:42. <http://www.cine-tarim.com.tr/dergi/arsiv42/sektorel04.htm>, 2002.
3. Atılğan, A. Seralarda Aşırı Gübre Kullanımı Çevreyi Tehdit Ediyor. Ekoloji Dergisi, <http://ekolojimagazin.com/?s=magazin&id=308>, 2007.
4. Topbaş, M.T, A.R. Brohi. ve M.R. Karaman. Çevre Kirliliği. T.C.Çevre Bakanlığı Yayınları. Ankara, 1998.
5. Koopman, R.C., Deliming with epsom salts. *J. Amer. Leather Chem. Ass.*, **77(7)**, 358-362, 1982.





6. Klaasse, M.J., CO<sub>2</sub> deliming. *J. Amer. Leather Chem. Ass.*, **85(11)**, 431-441, 1990.
7. Purushotham, H., Chandrababu, N.K., Khanna J.K., Raghavan, K.V., Carbon-dioxide deliming – An environmentally friendly option for Indian tanneries. *J. Soc. Leather Technol. Chem.*, **77(6)**, 183-195, 1993.
8. Güner, N.D., *Paliurus spina-christi* Mill. üzerinde farmakognozik araştırmalar. Hacettepe Üniversitesi Sağlık Bilimleri Enstitüsü Yüksek Lisans Tezi, Ankara ,2005
9. Gutierrez RM, Perez RL., *Raphanus sativus* (radish): their chemistry and biology. *ScientificWorldJournal* **4**:811–37, 2004.
10. Shukla S, Chatterji S, Mehta S, Rai PK, Singh RK, Yadav DK, Watal G. 2010. Antidiabetic effect of *Raphanus sativus* root juice. *Pharm Biol.*
11. Lugasi A, Blazovics A, Hagymasi K, Kocsis I, Kery A. Antioxidant effect of squeezed juice from black radish (*Raphanus sativus* L. var *niger*) in alimentary hyperlipidaemia in rats. *Phytother Res* **19(7)**:587–91, 2005..
12. Lugasi, A., Dworschak, E., Blazovics and A., Kery, A., Antioksidant and Free Radical Scavenging Properties of Squeezed Juice from Black Radish (*Raphanus sativus* L. var *niger*) Root. *Phytotherapy Research*, Vol. 12, 502-506, 1998.
13. Hanlon, P.R. and Barnes, D., M., Phytochemical Composition and Biological Activity of 8 Varieties of Radish (*Raphanus sativus* L.) Sprouts and Mature Taproots. *Journal of Food Science* V: 76, Nr:1, 2011 p: 192, 2011.
14. Hanlon, P.R., Webber, D. M. and Barnes, D., M., Aqueous Extract from Spanish Black Radish (*Raphanus sativus* L. var *niger*) Induces Detoxification Enzymes in the HepG2 Human Hepatoma Cell Line, *Journal of Agricultural and Food Chemistry*, 55, p: 6439-6446, 2007.
15. Ciska, E., Piskula, M., Waszczuk, K. and Kozłowska, H., Glucosinates in Cruciferous vegetables grown in Poland. In *Bioactive Substances in Food of Plant Origin* ed. by H. Kozłowska, J. Fornal and Z. Zdunczyk, pp.36-39. Polish Academy of Science, Olsztyn, 1994.
16. Fenwick, G. R., Heaney, R. K., and Mullin, W. J.. Glucosinolates and their breakdown products in food and food plants. *CRC Crit. Rev. Food Sci. Nutr.* 18, 123-201, 1983.
17. Wang LS, Sun XD, Cao Y, Wang L, Li FJ, Wang YF. Antioxidant and pro-oxidant properties of acylated pelargonidin derivatives extracted from red radish (*Raphanus sativus* var. *niger*, Brassicaceae). *Food Chem Toxicol* **48(10)**:2712–8, 2010.
18. Nakamura Y, Nakamura K, Asai Y, Wada T, Tanaka K, Matsuo T, Okamoto S, Meijer J, Kitamura Y, Nishikawa A, Park EY, Sato K, Ohtsuki K. Comparison of the glucosinolate-myrosinase systems among daikon (*Raphanus sativus*, Japanese white radish) varieties. *J Agric Food Chem* **56(8)**:2702–7, 2008.
19. Manici, L. M., Lazzeri L. And Palmieri S., In Vitro Fungitoxic Activity of some Glucosinolates and their Enzyme-Derived Products toward Plant Pathogenic Fungi, *J. Agric. Food Chem.* 45, 2768-2773, 1997.

## Acknowledgements

Mümin Çolakoğlu, Murat Kaplan, Demet Şahin, Ersin Önem, Ali Yorgancıoğlu, Asist. Prof. Hüseyin Ata Karavana and Dr. Deniz Kalender.